



ANTIFOULING COMPATIBILITY CHART

	Hard Antifouling	Durable Ablative	Soft Ablative	Modified Antifouling	Freshwater Antifouling
<div style="border: 1px solid black; padding: 5px; width: fit-content; margin-bottom: 10px;">Existing Bottom Paint</div> <div style="border: 1px solid black; padding: 5px; width: fit-content;">New Bottom Paint</div>	Baltoplate Bottomkote Aqua Bottom Pro Gold! BottomShield Defense Defense HC Epoxy Cop Sharkskin Talon Trinidad (All) Tropikote Ultra Ultra-Kote Unepoxy (All) VC Offshore	Cukote Hydrocoat (All) Horizons Micron CSC Micron Extra Micron Optima Neptune 5 PCA Gold! Trilux 33 Ultima SR-40 Ultima SR-60 Vivid	Ablative Plus AF-33 ACT Aqua-One Bottomkote NT CPP Micron CF Micron Optima Micron WA Monterey Pacifica Plus Proguard Ablative Smart Solution Super B Ablative Ultima Eco Armor	Biocop TF* Bottomkote Pro Micron 99* Micron 66* Seamate Ultima SSA Islands 44 TF* Tropikote EX* Islands 44 Plus* Biotin Plus*	FW 21 VC 17 SR 21
Black Widow™ The Protector™ Trinidad™ (All) Vivid™	Sand and Apply	Heavy Sand and Apply	Remove	Remove	Remove
ECO HRT™ Premium HRT™ Unepoxy HRT™	Sand and Apply	Light Sand and Apply	Light Sand and Apply	Sand and Apply	Remove
Horizons™ Ultima SR-40™ Ultima SR-60™ Barracuda™	Sand and Apply	Light Sand and Apply	Sand and Apply	Heavy Sand and Apply	Remove
Hydrocoat™ Hydrocoat SR™ Hydrocoat Eco™ Neptune HRT™	Light Sand and Apply	Powerwash and Apply	Light Sand and Apply	Sand and Apply	Sand and Apply
SR 21™	Sand and Apply	Remove	Remove	Remove	Clean and Apply

Bottomkote NT™, Aqua™, ACT™, Micron CSC™, Micron Optima™, Micron Extra™, Micron WA™, Proguard Ablative™, Micron 99™, Micron 66™, VC-17™, Baltoplate™, Epoxy Cop™, Ultra™, VC Offshore™ and Pacifica Plus™ refer to products sold by Interlux®. Armor™ refers to a product sold by Flexdel. Sharkskin™, Talon™, Tropikote™, Cukote™, Biocop TF™, Islands 44 TF™, Tropikote EX™, Islands 44 Plus™, Biotin Plus™, Monterey™, Smart Solution™, and AF33™ refer to products sold by New Nautical Coatings.

*Tin copolymer paints and certain additional modified antifouling paints should be sealed with a coat of 6627 Tie Coat Primer, allow to dry 4 hours and apply new antifouling paint. This document is intended as a guide only, additional preparation may be involved due to condition and age of substrate.