

ANTIFOULLING FOR OUTDRIVES

Pettit Paint offers several antifouling paints for outdrives but below are the suggested systems for each substrate. As with all paint systems, the quality of the product's adhesion depends on the surface to which it is applied. Make sure all surfaces are clean and properly prepared, as per the directions on the product's label. All previous surfaces should be in good condition in order to achieve proper adhesion. Further information can be found on our product data sheets or at www.amtcomposites.co.za

New Factory Painted Outdrives

1. Thoroughly scuff outdrive surface with 80-grit sandpaper, then solvent clean with 120 Brushing Thinner to remove residue.
2. Apply one coat of Pettit Protect Epoxy Primer and allow to dry the appropriate time, based on substrate temperature.
3. Apply two coats of Hydrocoat® Eco, Vivid®, Odyssey® Triton or Trinidad® XSR.

Previously Painted Outdrives

1. If the previous coating is in good condition, thoroughly sand with 80-grit sandpaper, then solvent clean with 120 Brushing Thinner to remove residue.
2. Apply one coat of Tie-Coat Primer and allow to dry four hours.
3. Apply two coats of Hydrocoat® Eco, Vivid®, Odyssey® Triton or Trinidad® XSR.

* If the previous coating is soft or in poor condition, remove to the bare surface by sanding or using a paint and varnish remover. Proceed with appropriate bare system as described below.

Bare Aluminium Outdrives

1. Abrade to clean, bright metal by sandblasting, or sanding with 60-grit sandpaper, then solvent clean with 120 Brushing Thinner to remove residue.
2. Apply two coats of Aluma-Protect Aluminium Epoxy Primer.
3. Apply two coats of Pettit Protect High Build Epoxy Primer.
4. Apply two coats of Hydrocoat® Eco, Vivid®, Odyssey® Triton or Trinidad® XSR.

Always read the labels or technical data sheets for all products specified herein before using.